

UNCLASSIFIED

AD 401 285

DEFENSE DOCUMENTATION CENTER

FOR

SCIENTIFIC AND TECHNICAL INFORMATION

CAMERON STATION, ALEXANDRIA, VIRGINIA



UNCLASSIFIED

NOTICE: When government or other drawings, specifications or other data are used for any purpose other than in connection with a definitely related government procurement operation, the U. S. Government thereby incurs no responsibility, nor any obligation whatsoever; and the fact that the Government may have formulated, furnished, or in any way supplied the said drawings, specifications, or other data is not to be regarded by implication or otherwise as in any manner licensing the holder or any other person or corporation, or conveying any rights or permission to manufacture, use or sell any patented invention that may in any way be related thereto.

401 285

STEP
24.1700
11.3900

43996

S/054/62/000/004/002/017
B101/B186

AUTHORS: Gitis, M. B., Mikhaylov, I. G., Khimunin, A. S.
TITLE: Apparatus for measuring the sonic velocity in liquid metals and melts.
PERIODICAL: Leningrad. Universitet. Vestnik. Seriya fiziki i khimii, no. 4, 1962, 52-55

TEXT: An apparatus working on the principle of electroacoustic feedback, able to measure ultrasonic velocity with the transducers in fixed positions is described here. Instead of the ultrasonic propagation velocity, the pulse repetition frequency is measured, i.e. the ultra-sound which has passed the test medium, is amplified, shaped, and again starts up the master pulse generator. The ultrasonic velocity is determined by $c=d/(1/f + \tau_{\Sigma})$, where d is the distance between the vibrators, f the pulse repetition frequency, τ_{Σ} the total electric and acoustic delay. To allow operation over a wide range of temperature the measuring cell has two delay rods. To eliminate the effect of the temperature gradient occurring in the delay rods,

Card 1/2

Apparatus for measuring the...

S/054/62/000/004/002/017
B101/B186

the ultrasonic propagation velocity is measured not only passing through the system but also in the reflection from the rod-fusion interfaces. $c = 2d f_1 f_2 / (2f_1 f_2 - f f_1 - f f_2)$, where f_1 and f_2 is the pulse repetition frequency in the two rods. The distance d is calibrated by a liquid of known sound conductivity. The pulse generator delivers negative pulses of 3 μ sec duration, 150 v amplitude, starting up a shock generator. Measurements are made with the precisely fixed frequency of 5 Mc/sec. The delay rods consist of fine-grained 1X18H9T (1Kh18N9T) steel. A check of the ultrasonic velocity in mercury between -39.2 and +70°C showed good agreement with the data found by O. J. Kleppa (Ultrasonic velocities of sound in some liquid metals. Adiabatic and isothermal compressibilities of liquid metals at their melting points. Journ. Chem. Phys., 18, 1331, 1950) and E. B. Freyer, J. C. Hubbard, D. W. Andrews (Sonic studies of the physical properties of liquids. Journ. Amer. Chem. Soc., 51, 759, 1929). There are 1 figure and 1 table.

SUBMITTED: May 22, 1962

Card 2/2